



Rubber-Like



TECHNICAL DATA SHEET			
	Cure >30 min.		Standards
Rubber Like	A90	A65	
Color	Black	Black/White	
Wavelength (nm)	395-405		
Viscosity (@25°C MPa·s)	550 (+/- 15)	1.100 (+/- 15)	
Density (g/cm ³)	1.10	1.10	
Tensile strength (MPa)	13	9	ASTDM D638
Tensile modulus (MPa)	65	40	ASTDM D638
Strain at break (%)	110	205	ASTDM D638
Hardness (Shore A)	90 (+/- 5)	65 (+/- 5)	/
Heat Deflection Temp. (°C)	50	/	ASTDM D638

Tensile ASTM D638 - Type V



SAFETY – WARNING

H302.Harmful if swallowed – H315.Causes skin irritation – H317.May cause an allergic skin reaction – H319.Causes serious eye irritation – H411.Toxic to aquatic life with long lasting effects – P261.Avoid breathing dust/fume/gas/mist/vapours/spray – P264. Wash arms, hands and face thoroughly after handling – P272.Contaminated work clothing should not be allowed out of the workplace – P273.Avoid release to the environment – P280.Wear protective gloves/protective clothing/eye protection/face protection – P305&P351&P338 IF IN EYE: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do. Continue rinsing – P302&352 IF ON SKIN: Wash with soap and water – P310.Immediately call a POISON CENTER or doctor/physician P501.Dispose of contents and container in accordance with all local, regional, national and International regulations